

52518

HDPE & LLDPE Injection Moulding , Extrusion Coating & Rotomoulding

Test/Composition	value	Unit	Method
Density	952 + 2	g/l	D 1505
Flexural Modulus	?1350	MPa	D 790
Izod 23°C	J25	J/m	D 256/A
MFR "E"	18+2	g/10 min	D 1238
Vicat	?122	°C	D 1525

Main Application: Housewares , High Fluidity

Product Type: HDPE Narrow MWD - Comopolymer Injection Moulding

Notes: Properties on compression moulded specimen according to method MA 17102, unless specified

Jam petrochemical company

021-55 15 1234

www.erisplast.ir

www.erisplast.com

Address: No. 68, Ghaffari Alley, East 15 Khordad St., Tehran