

HF4760(BL3)

HDPE

Test/Composition	value	Unit	Method
Density	0.95 6 +0.002	g/cm ³	ISO 1183
MFR(190°/21.16)	23+4	g/10min	ISO 1133
MFR(190°/5)	1.2z0.3	g/10min	ISO 1133
Notched Impact (23°C) ²	ñ9	mJ/mm ²	ISO179/1eA

Main Application: Small blow moulding

Notes:

1- FRR values are statistical and calculated by dividing MFR values.

2- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted is average values.

Jam petrochemical company

021-55 15 1234

www.erisplast.ir

www.erisplast.com

Address: No. 68, Ghaffari Alley, East 15 Khordad St., Tehran

erisplast

021-55 15 1234

www.erisplast.ir

www.erisplast.com

Address: No. 68, Ghaffari Alley, East 15 Khordad St., Tehran