

LH0075

LOW DENSITY POLYETHYLENE

MFI (190°C/2. 16 kg)	gr/10min.	0.75	ASTM D 1238
Density	gr/ml	0.92	* TSTM 209 B
Vicat softening point	oC	95	ASTM D 1525
Elongation @ break (MD)	%	300 min.	ASTM D 882
Elongation @ break (TD)	%	450 min.	ASTM D 882
Tensile @ break (MD)	kg/cm ²	170 min.	ASTM D 882
HDT	oC	33	ASTM D 648
Dart impact	gr	120 min.	ASTM D 1709

* TSTM = Toyo Soda Standard Test Method

LH0075 is a high molecular weight low density polyethylene film grade combining good flexible extrusion behavior and superior mechanical properties.

Film made from LH0075 exhibits high dart impact combined with excellent yield and tensile strength and high stiffness. It can be processed on automatic machines. It possesses good dimensional stability.

LH0075 is chiefly recommended for extrusion of blown film. It is suitable for shrink film having a high resistance to hole formation and high degree of shrinkage on cooling. LH0075 contains antioxidant.

Applications:

LH0075 is well suited for wide range of applications due to its unique balance of properties.

The superior mechanical properties will improve the functionality of the film.

Some examples are; carrier bags, shrink film, industrial film, dust bin liners, large bottles, blow moulding of small containers, packaging of pharmaceutical products, packaging of foodstuffs and bottles for storage of chemical products.

Bandar imam petrochemical company

021-55 15 1234

www.erisplast.ir

www.erisplast.com

Address: No. 68, Ghaffari Alley, East 15 Khordad St., Tehran

Erisplast

021-55 15 1234

www.erisplast.ir

www.erisplast.com

Address: No. 68, Ghaffari Alley, East 15 Khordad St., Tehran