

## Polyethylene Terephthalate BG 825

| Property                 | Test method       | Unit   | value           |
|--------------------------|-------------------|--------|-----------------|
| Intrinsic Viscosity (IV) | UBBELHODE         | dl/g   | $0.82 \pm 0.02$ |
| DEG content              | GC                | %Wt    | Max 2.0         |
| Color (CIE LAB)          | SPECTROSCOPY      | L*     | ≥ 90            |
|                          | SPECTROSCOPY      | B*     | ≤2.0            |
| Carboxyl End Groups      | AUTO<br>TITRATION | meq/kg | Max 32          |
| Melting Point            | DSC               | °C     | 249 ±2          |
| Acetaldehyde (AA)        | HEAD SPACE-<br>GC | ppm    | Max 1.0         |
| Water content            | KARL-FISHER       | %wt    | Max 0.3         |

<sup>\*</sup> Typical values not to be construed as specifications.

Product Description: Polyethylene Terephthalate bottle grade chips (highly viscous) is a condensation polymer produced by a continuous meltphase polymerization process followed by a solid state polymerization process, with an I.V of 0.75-0.85. The products has an excellent transparency and gloss, an outstanding gas barrier against oxygene and carbon dioxide, and outstanding toughness and impact strength.

Applications: CSD specially for tropical conditions • Carbonated Water • Large Bottles • Agrochemicals • APET Sheet • Strapping.

Tondgooyan petrochemical company

021-55 15 1234

www.erisplast.ir www.erisplast.com

Address: No. 68, Ghaffari Alley, East 15 Khordad St., Tehran.